

Blindbolt design resistances for use with BS 5950 and BS EN 1993

Report to: Henry Venables products Ltd

Document: RT1835

Version: 04

Date: October 2020



SCI (the Steel Construction Institute) has been a trusted, independent source of information and engineering expertise globally for over 30 years, and is one of the leading, independent providers of technical expertise and disseminator of best practice to the steel construction sector.

We support everyone involved in steel construction; from manufacturers, consulting and design engineers, architects, product developers to industry groups.

Version	Date	Purpose	Author	Reviewer	Approved
01	03/20	Issue to client	DGB		
02	06/20	Updated with final material test results	DGB		
03	06/20	Updated with M8 carbon steel tension results	DGB		
04	10/20	Property class for nuts added	DGB		

Although all care has been taken to ensure that all the information contained herein is accurate, The Steel Construction Institute assumes no responsibility for any errors or misinterpretations or any loss or damage arising therefrom.



EXECUTIVE SUMMARY

In January 2020, comprehensive physical testing of carbon steel and stainless steel Blindbolts was undertaken, supplementing previous testing completed in 2009.

Design resistances in shear and tension have been determined in accordance with BS EN 1990 for use with BS 5950 and BS EN 1993. There is no change to the 2009 guidance that bearing resistance should be calculated in the same way as for ordinary bolts, and that bolts in combined shear and tension should conform to the codified interaction expressions.

Design shear resistances are presented in the following table. In all cases the shear resistance is through the slotted portion of the assembly, with the toggle parallel to the line of the force.

	Shear resistance (kN)			
	Carbor	n steel	Stainless	steel
Bolt diameter	BS 5950	EC3	BS 5950	EC3
M8	7.9	9.1	6.5	7.8
M10	15.8	19.0	11.1	13.3
M12	22.0	26.4	15.4	18.4
M14	29.0	29.0		
M16	43.0	49.1	30.1	36.1
M20	63.4	76.1		
M24	87.8	105.4		
M30	137.2	164.6		

Design tensile resistances are presented in the following table.

	Tension resistance (kN)			
	Carbor	steel	Stainless	steel
Bolt diameter	BS 5950	EC3	BS 5950	EC3
M8	9.8	9.8	5.3	5.3
M10	14.1	14.1	12.7	12.7
M12	22.4	22.4	21.4	22.0
M14	34.8	34.8		
M16	38.8	38.8	42.8	42.9
M20	71.4	71.4		
M24	116.7	116.7		
M30	174.5	174.5		



In combined bending and shear, the interaction expressions presented in BS 5950 and in BS EN 1993-1-8 should be used, substituting the design resistances given in the preceding tables.

The bearing resistance according to BS 5950 should be calculated in the normal way, using an effective diameter equal to the nominal diameter of the Blindbolt, less the width of the slot.

The bearing resistance according to BS EN 1993-1-8 should be calculated in the normal way, using the nominal diameter of the Blindbolt.





Contents

		Page No
EXE	CUTIVE SUMMARY	iii
1	Blindbolts 1.1 Product supply 1.2 Product form, dimensions and material 1.3 Physical testing	1 1 1 3
2	Shear tests 2.1 Carbon steel bolts in shear 2.2 Stainless steel bolts in shear	4 4 9
3	Tension tests 3.1 Carbon steel bolts in tension 3.2 Stainless steel bolts in tension	13 15 18
4	Bearing resistance 4.1 Bearing resistance to BS 5950 4.2 Bearing resistance to BS EN 1993-1-8	22 22 23
5	Combined shear and tension	24
6	REFERENCES	26
Appe	endix A Test data and resistance calculations – carbon steel shear resistances	27
Арре	endix B Test data and resistance calculations – stainless steel shear resistances	s 35
Арре	endix C Test data and resistance calculations – carbon steel tensile resistances	39
Appe	endix D Test data and resistance calculations – stainless steel tensile resistance	es 47





1 Blindbolts

1.1 Product supply

Blindbolts covered by this report are supplied by:

Henry Venables Products Ltd UK Head Office The Woodhouse Hopton Wafers Kidderminster Worcester DY12 0EE United Kingdom

1.2 Product form, dimensions and material

The blind bolts covered by this report have the form shown in Figure 1.1




Figure 1.1 Blind bolt

Blind bolts from Henry Venables Products Ltd, UK, are manufactured in property class 10.9 carbon steel (ultimate strength 1000 N/mm²; yield strength 900 N/mm²) and in A4-70 stainless steel (ultimate strength 700 N/mm²; 450 N/mm² at 0.2% elongation). For carbon



steel bolts property class 8 nuts are used with M8 to M20 and property class 10 nuts with M24 and M30.

The (2020) range of carbon steel blind bolts is presented in Table 1.1.

Table 1.1 Carbon steel blind bolts

Product Code	Diameter (mm)	Length (mm)
BB0850DTASM	8	50
BB1060DTASM	10	60
BB1095DTASM	10	95
BB10130DTASM	10	130
BB1270DTASM	12	70
BB12120DTASM	12	120
BB12180DTASM	12	180
GBB1475DTASM	14	75
GBB14125DTASM	14	125
GBB14185DTASM	14	185
GBB1690DTASM	16	90
GBB16130DTASM	16	130
GBB16180DTASM	16	180
GBB20110DTASM	20	110
GBB20140DTASM	20	140
GBB201800DTASM	20	180
GBB20250DTASM	20	250
GBB24130DTASM	24	130
GBB30140DTASM	30	140

The (2020) range of stainless steel blind bolts is presented in Table 1.2.

Table 1.2 Stainless steel blind bolts

Product Code	Diameter (mm)	Length (mm)
BB0850A4ASM	8	50
BB1060A4ASM	10	60
BB1290A4ASM	12	90
GBB16100A4ASM	16	100



The bolt dimensions and calculated shear and tensile areas are presented in Table 1.3. It should be noted that the pin plays no part in resisting tensile loads – the toggle bears on the end of the machined slot in the blot shank.

Table 1.3 Bolt dimensions and areas

Bolt diameter	Slot width (mm)	Pin diameter (mm)	Shear area (mm²)	Tensile area (mm²)
M8 carbon	4	1.0	19.7	15.7
M8 stainless	3.5	1.0	23.2	18.7
M10	4	1.6	39.6	30.1
M12	5	1.6	54.9	43.7
M14	6	1.8	72.6	58.3
M16	6	2.0	107.4	87.4
M20	8	2.0	158.5	134.6
M24	10	2.0	219.5	191.6
M30	12.5	3.2	343.0	287.2

1.3 Physical testing

Physical testing of Blindbolts in carbon steel and stainless steel, as supplied by Henry venables Products Ltd was completed in January and February of 2020, by:

Intertek NDT (Materials Testing) 99 Victory Road Derby DE24 8ZF United Kingdom

Intertek NDT are an ISO/IEC 17025 UKAS accredited metallurgical test laboratory.



2 Shear tests

Four samples of each assembly were tested in a simple lap joint arrangement, as shown in Figure 2.1.

In every case, the thickness of the plates were arranged so that the shear plane was through the slotted region of the bolt.

In every case, the toggle (and slot) were parallel to the applied load.




Figure 2.1 Static shear test arrangement

The dimensions of the bolts were verified to an accuracy of 0.01 mm.

For each bolt diameter, material strengths were established by test.

2.1 Carbon steel bolts in shear

Section 2.1.1 presents a fully worked example of the input data and calculation procedure undertaken in accordance with BS EN 1990¹ used to establish the shear resistance.



Section 2.1.4 summarises the results from all bolt diameters. In each case, the same process was used to determine the bolt diameters.

Figure 2.2 shows the plot of load against deformation for a typical carbon steel bolt tested in shear. The specific test was M16, Test 2.




Figure 2.2 Typical carbon steel shear test (M16, test 2)

Figure 2.3 shows the plot of load against deformation for a typical stainless steel bolt tested in shear. The specific test was M12, Test 2.






Figure 2.3 Typical stainless steel shear test (M12, test 2)

2.1.1 M20 carbon steel blind bolt in shear

2.1.1.1 Material strength

The ultimate strength determined by test is shown in Table 2.1.

Table 2.1 M20 material strength

	Ultimate strength (N/mm²)
	1125
	1072
	1077
Average	1091

2.1.1.2 Bolt diameter

Measured diameters are shown in Table 2.2.



Table 2.2 M20 measured bolt diameters

Diameter (mm)	Diameter (mm)
19.92	19.98
19.97	19.99
20.02	20.02
19.98	19.99
19.97	20.03
20.00	20.01
Average	19.99

2.1.1.3 Shear resistance

Failure loads are recorded in Table 2.3.

Table 2.3 M20 measured shear resistance

Test	Test resistance (kN)
1	107.73
2	102.23
3	103.21
4	100.55

2.1.1.4 Tested capacity adjustment

The tested capacity has been normalised to allow for the measured material strength and measured diameter by the following factor:

$$\alpha_{\rm v} = \frac{[df_{\rm u}]_{\rm Specified}}{[df_{\rm u}]_{\rm Measured}} = \frac{20 \times 1000}{19.99 \times 1091} = 0.917$$

2.1.1.5 Normalised test resistance

The normalised resistances are shown in Table 2.4.



Table 2.4 M20 normalised shear resistance

Test	Normalised shear resistance (kN)
1	98.76
2	93.80
3	94.62
4	92.18
Mean	94.84
Standard deviation	2.80
Coefficient of variation	3.0%

2.1.1.6 Ultimate resistance to BS EN 1990

The ultimate design shear resistance has been calculated in accordance with BS EN 1990, Annex D.

Previous tests have established the anticipated coefficient of variation, so $k_{d,n}$ is taken from Table D2 for " V_x known", for 32 tests (value taken for 30), as 3.13.

Therefore:

Design shear resistance = $94.84 - 3.13 \times 2.8 = 86.1 \text{ kN}$

2.1.2 Resistance calculations in accordance with BS 5950²

The design shear resistance should not more than that calculated in accordance with clause 6.3.2.1, where:

 $P_s = p_s A_s$ where $p_s = 400 \text{ N/mm}^2$ from Table 30 of BS 5950.

From Table 1.3, $A_s = 158.5 \text{ mm}^2$ for an M20 Blindbolt.

Therefore:

$$P_{\rm s} = 400 \times 158.5 \times 10^{-3} = 63.4 \text{ kN}$$

2.1.3 Resistance calculations in accordance with BS EN 1993-1-83

The design shear resistance should not more than that calculated in accordance with Table 3.4, where:

$$F_{\rm v,Rd} = \frac{0.6 f_{
m ub} A}{\gamma_{
m M2}}$$
, where $f_{
m ub}$ = 1000 N/mm² for property class 10.9 bolts and $\gamma_{
m M2}$ = 1.25

From Table 1.3, $A_s = 158.5 \text{ mm}^2$ for an M20 Blindbolt.

Therefore:

$$F_{\text{v,Rd}} = \frac{0.6 \times 1000 \times 158.5}{1.25} \times 10^{-3} = 76.1 \text{ kN}$$



In this example, the resistance is set by the calculated results in accordance with the design standard. The final design resistances are:

BS 5950: 63.4 kN

BS EN 1993-1-9: 76.1 kN

2.1.4 Carbon bolt shear resistance summary

Table 2.5 presents the shear resistances for carbon steel blind bolts, following the process shown in the preceding sections. Calculations for each bolt diameter are presented in Appendix A.

Table 2.5 Carbon steel Blindbolt shear resistance

Bolt Diameter	Shear resistance (kN)	
	BS 5950	BS EN 1993-1-8
M8	7.9	9.1
M10	15.8	19.0
M12	22.0	26.4
M14	29.0	34.8
M16	43.0	49.1
M20	63.4	76.1
M24	87.8	105.4
M30	137.2	164.6

2.2 Stainless steel bolts in shear

Section 2.2.1 presents a fully worked example of the input data and calculation procedure undertaken in accordance with BS 5950 and BS EN 1993-1-8. There is no modification given in BS EN 1993-1-4⁴ for stainless steel.

Section 2.2.2 summarises the results from all bolt diameters. In each case, the same process was used to determine the bolt diameters.

2.2.1 M12 stainless steel blind bolt in shear

2.2.1.1 Material strength

The ultimate strength determined by test is shown in Table 2.6.



Table 2.6 M12 material strength

	Ultimate strength (N/mm²)
	775
	776
	792
Average	781

2.2.1.2 Bolt diameter

Measured diameters are shown in Table 2.7.

Table 2.7 M12 measured bolt diameters

Diameter (mm)	Diameter (mm)
11.98	11.92
11.96	11.94
11.93	11.94
11.94	11.94
11.95	11.95
11.95	11.95
Average	11.95

2.2.1.3 Shear resistance

Failure loads are recorded in Table 2.8.

Table 2.8 M12 measured shear resistance

Test	Test resistance (kN)
1	34.40
2	34.22
3	33.80
4	33.92

2.2.1.4 Tested capacity adjustment

The tested capacity has been normalised to allow for the measured material strength and measured diameter by the following factor:

$$\alpha_{\rm v} = \frac{[df_{\rm u}]_{\rm Specified}}{[df_{\rm u}]_{\rm Measured}} = \frac{12 \times 700}{11.95 \times 781} = 0.900$$



2.2.1.5 Normalised test resistance

The normalised resistances are shown in Table 2.9.

Table 2.9 M12 normalised shear resistance

Test	Normalised shear resistance (kN)
1	30.97
2	30.81
3	30.43
4	30.54
Mean	30.69
Standard deviation	0.25
Coefficient of variation	0.8%

2.2.1.6 Ultimate resistance to BS EN 1990

The ultimate design shear resistance has been calculated in accordance with BS EN 1990, Annex D.

Previous tests have established the anticipated coefficient of variation, so $k_{d,n}$ is taken from Table D2 for " V_x known", for 16 tests (value taken for 10), as 3.23

Therefore:

Design shear resistance = $30.69 - 3.23 \times 0.25 = 29.9$ kN

2.2.2 Resistance calculations in accordance with BS 5950

The design shear resistance should not more than that calculated in accordance with clause 6.3.2.1, where:

$$P_s = p_s A_s$$
 where $p_s = 0.4 f_u$ and $f_u = 700 \text{ N/mm}^2$.

From Table 1.3, $A_s = 54.9 \text{ mm}^2$ for an M12 Blindbolt.

Therefore:

$$P_{\rm s} = 0.4 \times 700 \times 54.9 \times 10^{-3} = 15.4 \text{ kN}$$

2.2.3 Resistance calculations in accordance with BS EN 1993-1-8

The design shear resistance should not more than that calculated in accordance with Table 3.4, where:

$$F_{
m v,Rd} = rac{0.6 f_{
m ub} A}{\gamma_{
m M2}}$$
, where $f_{
m ub}$ = 700 N/mm² for property class 70 bolts and $\gamma_{
m M2}$ = 1.25

From Table 1.3, $A_s = 54.9 \text{ mm}^2$ for an M12 Blindbolt.

Therefore:



$$F_{\rm v,Rd} = \frac{0.6 \times 700 \times 54.9}{1.25} \times 10^{-3} = 18.5 \text{ kN}$$

In this example, the resistance is set by the calculated results in accordance with the design standard. The final design resistances are:

BS 5950: 15.4 kN

BS EN 1993-1-8: 18.5 kN

2.2.4 Stainless steel bolt shear resistance summary

Table 2.10 presents the design shear resistances for stainless steel blind bolts following the process shown in the preceding sections. Calculations for each bolt diameter are presented in Appendix B.

Table 2.10 Stainless steel Blindbolt shear resistance

Bolt Diameter	Shear resistance (kN)	
	BS 5950	BS EN 1993-1-8
M8	6.5	7.8
M10	11.1	13.3
M12	15.4	18.4
M16	30.1	36.1



3 Tension tests

Testing was completed using the test apparatus shown in Figure 3.1. Tension in the bolts is produced by applying compression to the interlocking fabricated assemblies.



Figure 3.1 Static tension test arrangement

The dimensions of the bolts were verified to an accuracy of 0.01 mm.

For each bolt diameter, material strengths were established by test.

Figure 3.2 shows the plot of load against deformation for a typical carbon steel bolt tested in tension. The specific test was M16, Test 2.






Figure 3.2 Typical carbon steel tension test (M16, test 2)

Figure 3.3 shows the plot of load against deformation for a typical stainless steel bolt tested in tension. The specific test was M12, Test 2.





Figure 3.3 Typical stainless steel tension test (M12, test 2)

3.1 Carbon steel bolts in tension

Section 3.1.1 presents a fully worked example of the input data and calculation procedure undertaken in accordance BS EN 1990.

Section 3.1.4 summarises the results from all bolt diameters. In each case, the same process was used to determine the bolt diameters.

3.1.1 M20 carbon steel blind bolt in tension

3.1.1.1 Material strength

The ultimate strength determined by test is shown in Table 3.1.

Table 3.1 M20 material strength

	Ultimate strength (N/mm²)
	1125
	1072
	1077
Average	1091



3.1.1.2 Bolt diameter

Measured diameters are shown in Table 3.2.

Table 3.2 M20 measured bolt diameters

Diameter (mm)	Diameter (mm)
19.92	19.98
19.97	19.99
20.02	20.02
19.98	19.99
19.97	20.03
20.00	20.01
Average	19.99

3.1.1.3 Tension resistance

Failure loads are recorded in Table 3.3.

Table 3.3 M20 measured tension resistance

Test	Test resistance (kN)
1	82.22
2	83.29
3	79.78
4	80.78
5	82.44
6	82.02

3.1.1.4 Tested capacity adjustment

The tested capacity has been normalised to allow for the measured material strength and measured diameter by the following factor:

$$\alpha_{\rm t} = \frac{\left[d^2 f_{\rm u} \right]_{\rm Specified}}{\left[d^2 f_{\rm u} \right]_{\rm Actual}} = \frac{20^2 \times 1000}{19.99^2 \times 1091} = 0.918$$

3.1.1.5 Normalised test resistance

The normalised resistances are shown in Table 3.4.



Table 3.4 M20 normalised tensile resistance

Test	Normalised tensile resistance (kN)
1	75.41
2	76.40
3	73.18
4	74.09
5	75.62
6	75.23
Mean	74.99
Standard deviation	1.16
Coefficient of variation	1.5%

3.1.1.6 Ultimate resistance to BS EN 1990

The ultimate design tension resistance has been calculated in accordance with BS EN 1990, Annex D.

Previous tests have established the anticipated coefficient of variation, so $k_{d,n}$ is taken from Table D2 for " V_x known", for 48 tests (taken as 30), as 3.13

Therefore:

Design tensile resistance = $74.99 - 3.13 \times 1.16 = 71.4 \text{ kN}$

3.1.2 Resistance calculations in accordance with BS 5950

The design tensile resistance should not more than that calculated in accordance with clause 6.3.4.3, where:

 $P_t = p_t A_t$ where $p_t = 700 \text{ N/mm}^2$ from Table 34 of BS 5950

From Table 1.3, $A_s = 134.6 \text{ mm}^2$ for an M20 Blindbolt.

Therefore:

$$P_1 = 700 \times 134.6 \times 10^{-3} = 94.2 \text{ kN}$$

3.1.3 Resistance calculations in accordance with BS EN 1993-1-8

The design tensile resistance should not more than that calculated in accordance with Table 3.4, where:

$$F_{\rm t,Rd} = {0.9 f_{
m ub} A_{
m S} \over \gamma_{
m M2}}$$
 , where $f_{
m ub}$ = 1000 N/mm² for property class 10.9 bolts and $\gamma_{
m M2}$ = 1.25

From Table 1.3, A_s is the tensile area, = 134.6 mm² for an M20 Blindbolt.

Therefore:



$$F_{t,Rd} = \frac{0.9 \times 1000 \times 134.6}{1.25} \times 10^{-3} = 96.9 \text{ kN}$$

In this example, the resistance is set by the tested resistance calculated in accordance with BS EN 1990. The final design resistances are:

BS 5950: 71.3 kN

BS EN 1993-1-8: 71.3 kN

3.1.4 Carbon bolt tensile resistance summary

Table 3.5 presents the design tensile resistances for carbon steel blind bolts following the process shown in the preceding sections. Calculations for each bolt diameter are presented in Appendix C.

Table 3.5 Carbon steel Blindbolt tensile resistance

Bolt Diameter	Tensile resistance (kN)	
	BS 5950	BS EN 1993-1-8
M8	9.8	9.8
M10	14.1	14.1
M12	22.4	22.4
M14	34.8	34.8
M16	38.8	38.8
M20	71.4	71.4
M24	116.7	116.7
M30	174.5	174.5

3.2 Stainless steel bolts in tension

Section 3.2.1 presents a fully worked example of the input data and calculation procedure undertaken in accordance with BS EN 1990.

Section 3.2.4 summarises the results from all bolt diameters. In each case, the same process was used to determine the bolt diameters.

3.2.1 M12 stainless steel blind bolt in tension

3.2.1.1 Material strength

The ultimate strength determined by test is shown in Table 3.6.



Table 3.6 M12 material strength

	Ultimate strength (N/mm²)
	775
	776
	792
Average	781

3.2.1.2 Bolt diameter

Measured diameters are shown in Table 3.7.

Table 3.7 M12 measured bolt diameters

Diameter (mm)	Diameter (mm)
11.98	11.92
11.96	11.94
11.93	11.94
11.94	11.94
11.95	11.95
11.95	11.95
Average	11.95

3.2.1.3 Tension resistance

Failure loads are recorded in Table 3.8.

Table 3.8 M12 measured tension resistance

Test	Test resistance (kN)
1	26.61
2	26.87
3	25.91
4	27.36
5	25.89
6	25.73

3.2.1.4 Tested capacity adjustment

The tested capacity has been normalised to allow for the measured material strength and measured diameter by the following factor:



$$\alpha_{\rm t} = \frac{\left[a^2 f_{\rm u}\right]_{\rm Specified}}{\left[a^2 f_{\rm u}\right]_{\rm Actual}} = \frac{12^2 \times 700}{11.95^2 \times 1781} = 0.904$$

3.2.1.5 Normalised test resistance

The normalised resistances are shown in Table 3.9.

Table 3.9 M12 normalised tensile resistance

Test	Normalised tensile resistance (kN)
1	24.07
2	24.30
3	23.43
4	24.75
5	23.42
6	23.27
Mean	23.87
Standard deviation	0.59
Coefficient of variation	2.5%

3.2.1.6 Ultimate resistance to BS EN 1990

The ultimate design tension resistance has been calculated in accordance with BS EN 1990, Annex D.

Previous tests have established the anticipated coefficient of variation, so $k_{d,n}$ is taken from Table D2 for " V_x known", for 24 tests (value taken as 20), as 3.16

Therefore:

Design tensile resistance = $23.87 - 3.16 \times 0.59 = 22.0 \text{ kN}$

3.2.2 Resistance calculations in accordance with BS 5950

The design tensile resistance should not more than that calculated in accordance with clause 6.3.4.3, where:

 $P_t = p_t A_t$ where $p_t = 0.7 U_b$, where $U_b = 700 \text{ N/mm}^2$ for a property class 70 bolt.

From Table 1.3, $A_s = 43.7 \text{ mm}^2$ for an M12 Blindbolt.

Therefore:

$$P_1 = 0.7 \times 700 \times 43.7 \times 10^{-3} = 21.4 \text{ kN}$$

3.2.3 Resistance calculations in accordance with BS EN 1993-1-8

The design tension resistance should not more than that calculated in accordance with Table 3.4, where:



$$F_{\rm t,Rd} = \frac{0.9 f_{\rm ub} A_{\rm s}}{\gamma_{\rm M2}}$$
, where $f_{\rm ub}$ = 700 N/mm² for property class 70 bolts and $\gamma_{\rm M2}$ = 1.25

From Table 1.3, A_s is the tensile area, = 43.7 mm² for an M12 Blindbolt.

Therefore:

$$F_{\rm t,Rd} = \frac{0.9 \times 700 \times 43.7}{1.25} \times 10^{-3} = 22.0 \text{ kN}$$

In this example, the resistance is set by the tested resistance calculated in accordance with BS 5950, and by that calculated in accordance with BS EN 1990 for Eurocode design. The final design resistances are:

BS 5950: 21.4 kN

BS EN 1993-1-8: 22.0 kN

3.2.4 Stainless steel bolt tension resistance summary

Table 3.5 presents the design tension resistances for stainless steel blind bolts following the process shown in the preceding sections. Calculations for each bolt diameter are presented in Appendix D.

Table 3.10 Stainless steel Blindbolt tensile resistance

Bolt Diameter	Tensile resistance (kN)			
	BS 5950	BS EN 1993-1-8		
M8	5.3	5.3		
M10	12.7	12.7		
M12	21.4	22.0		
M16	42.8	42.9		



4 Bearing resistance

No specific bearing tests were undertaken in 2020, as successive tests since 2009 have shown that the rules proposed in RT 1303 are satisfactory. The tests undertaken in 2020 have been used to verify the original recommendations. An example calculation to BS 5950 is presented in section 4.1, and to BS EN 1993-1-8 presented in section 4.2.

4.1 Bearing resistance to BS 5950

The expression for bearing capacity in BS 5950 was prepared to limit deformation at working load (SLS) to approximately 1.5 mm.

RT 1303 proposed that the BS 5950 expression in clause 6.3.3.3 could be adopted for a Blindbolt, using an effective diameter equal to the nominal diameter, less the width of the slot.

One of the M16 shear tests has been used to examine the appropriateness of the proposal in RT 1303.

The M16 bolts were tested in an 8 mm thick plate, grade S355. The slot in an M16 is given in Table 1.3 as 6 mm.

The effective diameter is therefore 16 - 6 = 10 mm.

According to Table 32 of BS 5950, the bearing strength of the connected part is 550 N/mm² for grade S355 material.

Thus, according to clause 6.3.3.3, the bearing capacity P_{bs} is given by:

$$P_{\rm bs} = 1.0 \times 10 \times 8 \times 550 \times 10^{-3} = 44 \text{ kN}$$

This is approximately equivalent to a working load of $^{44}/_{1.5}$ = 29 kN

Figure 4.1 shows the load-deformation plot for a typical M16 shear test, with a horizontal line at 29 kN. The deformation from an initial application of load is approximately 1.5 mm.

For design according to BS 5950, the bearing resistance may therefore be calculated based on an effective diameter of nominal diameter less the slot width.






Figure 4.1 Typical carbon steel tension test (M16, test 2) with bearing capacity

4.2 Bearing resistance to BS EN 1993-1-8

In contrast to BS 5950, BS EN 1993-1-8 places no limit on deformation and bearing resistances are much higher.

RT 1303 proposed that for design to BS EN 1993-1-8, bearing resistance be calculated in the normal way, using the nominal bolt diameter.

According to Table 3.4, for bolts not influenced by edge, end, pitch or gauge dimensions, the design bearing resistance is given by:

$$F_{\text{b,Rd}} = \frac{2.5 \times 1.0 \times 470 \times 16 \times 8}{1.25 \times 10^3} = 120 \text{ kN}$$

Based on the measured plate properties, the tested resistance would be expected to be:

$$F_{\rm b,Rd} = \frac{2.5 \times 1.0 \times 550 \times 16 \times 8}{10^3} = 176 \text{ kN}$$

As can be seen, this is greatly in excess of the shear resistance of the bolt (approximately 65 kN in Figure 4.1). The bearing resistance for calculations according to BS EN 1993-1-8 should be calculated using the normal rules and the nominal diameter of the bolt.



5 Combined shear and tension

Bolts subjected to combined shear and tension were tested in 2009, in the apparatus shown in Figure 5.1.



Figure 5.1 Test equipment for bolts subject to combined shear and tension

As the 2020 tests show no significant change in behaviour from the 2009 results, no change is proposed to the use of the rules presented in the design standards. In design to both BS 5950 and BS EN 1993-1-8 the shear capacity ('resistance') and the tension capacity ('resistance') used in the interaction expressions should be the values presented in this report for Blindbolts with a slot.





6 REFERENCES

- 1 BS EN 1990:2002 + A1:2005 incorporating corrigendum December 2008 Eurocode – Basis of structural design BSI, 2009
- BS 5950-1:2002 incorporating corrigendum No. 1 and Amendment No.1 Structural use of steelwork in building – Part 1: Code of practice for design – Rolled and welded sections BSI, 2007 (Withdrawn)
- 3 BS EN 1993-1-8:2005 incorporating corrigenda Dec 2005, Sep 2006, July 2009 and Aug 2010 Eurocode3: Design of steel structures Part 1-8: Design of joints BSI, 2010
- 4 BS EN 1993-1-4:2006 + A1:2015
 Eurocode 3 Design of steel structures Part 1-4: General rules –
 Supplementary rules for stainless steels
 BSI, 2015



Appendix A Test data and resistance calculations – carbon steel shear resistances

M8 carbo	n steel				
material strength		(N/mm^2)		measured diameters (mm	
		1155		8.01	7.93
		1149		7.90	7.89
		1165		7.92	7.98
Average	_	1156	_	7.92	7.91
				7.92	7.92
				7.92	7.94
				Average	7.93
Adjustment factor, $\alpha_{\rm v}$		0.872		Shear area	19.7 mm²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 resistance	
1	11.32	9.88			7.9 kN
2	12.16	10.61			
3	11.45	9.99		EN 1993-1-	8 resistance
4	11.99	10.46			9.5 kN
	Mean	10.23			
Stand	Standard deviation				
Coefficient of variation		3.5%			
	$k_{d,n}$	3.13			
ULS Desig	gn resistance	9.1	kN		
				BS 5950	7.9 kN
				EN 1993-1-8	9.1 kN



M10 carbo	n steel					
material strength		(N/mm²)		measured diameters (mm)		
		997		9.88	9.81	
		1009		9.81	9.87	
		1038		9.82	9.87	
Average		1015		9.85	9.83	
				9.83	9.81	
				9.87	9.87	
				Average	9.84	
Adjustment factor, $lpha_{ ext{ iny }}$		1.000		Shear area	39.6 mm ²	
		normalised				
	test shear	shear				
Test	resistance	resistance				
number	(kN)	(kN)	_	BS 5950 resistance		
1	26.07	26.07			15.8 kN	
2	25.25	25.25				
3	25.02	25.02		EN 1993-1-8	resistance	
4	23.48	23.48			19.0 kN	
	Mean	24.96				
Standa	ard deviation	1.08				
Coefficient of variation		4.3%				
	$k_{d,n}$	3.13				
ULS Desig	n resistance	21.6	kN			
				BS 5950	15.8 kN	
0.9)	EN 1993-1-8	19.0 kN		



M12 carbon steel

material str	rength	(N/mm^2)		measured o	diameters (mm)
	-	1084		11.91	11.82
		1114		11.96	11.97
		1095		11.94	12.03
Average	•	1098	-	11.93	11.89
· ·				11.96	11.90
				11.90	11.91
				Average	11.93
Adjustment	factor, $\alpha_{\rm v}$	0.917		Shear area	54.9 mm
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 re	sistance
1	34.77	31.87	-		22.0 kN
2	33.65	30.84			
3	33.18	30.41		EN 1993-1-	-8 resistance
4	33.87	31.05			26.4 kN
	Mean	31.04			
Standa	ard deviation	0.61			
Coefficient	of variation	2.0%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	29.1	kN		
				BS 5950	22.0 kN

EN 1993-1-8

26.4 kN



M14 carbo	n steel				
material st	rength	(N/mm^2)		measured d	liameters (mm)
		1065		13.96	13.92
		1069		13.98	13.98
	_	1082	_	13.96	14.00
Average	_	1072		13.98	13.95
				14.00	14.01
				13.98	13.98
				Average	13.98
Adjustment	t factor, $\alpha_{\rm v}$	0.935		Shear area	72.6 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	44.98	42.03			29.0 kN
2	51.06	47.72			
3	48.59	45.41		EN 1993-1-	8 resistance
4	44.76	41.83			34.8 kN
	Mean	44.25			
Standa	ard deviation	2.84			
Coefficient	of variation	6.4%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	35.4	kN		
323 26316		55. 1	•		
				BS 5950	29.0 kN

EN 1993-1-8 34.8 kN



M16 carbo	n steel				
material str	ength	(N/mm ²)		measured d	liameters (mm)
		1174		15.63	15.98
		1197		15.97	15.97
		1186		15.98	15.99
Average	_	1186	_	15.97	15.96
				15.92	15.99
				15.94	15.98
				Average	15.94
Adjustment	factor, $lpha_{ m v}$	0.847		Shear area	107.4 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	62.00	52.49	-		43.0 kN
2	63.84	54.05			
3	66.36	56.18		EN 1993-1-	8 resistance
4	66.40	56.21			51.6 kN
	Mean	54.73			
Standa	rd deviation	1.81			
Coefficient	of variation	3.3%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	49.1	kN		

43.0 kN

49.1 kN

BS 5950 EN 1993-1-8



M20 carbo	n steel				
material st	rength	(N/mm^2)		measured d	liameters (mm)
		1125		19.92	19.98
		1072		19.97	19.99
	_	1077	_	20.02	20.02
Average	_	1091	=	19.98	19.99
				19.97	20.03
				20.00	20.01
				Average	19.99
Adjustmen	t factor, $\alpha_{ m v}$	0.917		Shear area	158.5 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	107.73	98.76			63.4 kN
2	102.32	93.80			
3	103.21	94.62		EN 1993-1-	8 resistance
4	100.55	92.18			76.1 kN
	Mean	94.84			
	ard deviation	2.80			
Coefficien	t of variation	3.0%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	86.1	kN		
				BS 5950	63.4 kN

76.1 kN



M24 carbo	n steel				
material st	rength	(N/mm^2)		measured d	iameters (mm)
		1090		23.91	23.92
		1063		23.88	23.98
		1093		23.92	23.93
Average	_	1082	_	23.94	23.93
				23.90	23.92
				23.94	23.92
				Average	23.92
Adjustmen	t factor, $\alpha_{\rm v}$	0.927		Shear area	219.5 mm ²
•	•				
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	152.2	141.11	_		87.8 kN
2	146.8	136.10			
3	144.35	133.83		EN 1993-1-	8 resistance
4	139.49	129.33			105.4 kN
	Mean	135.09			
Standa	ard deviation	4.90			
Coefficient	t of variation	3.6%			
ULS Desig	n resistance	135.1	kN		
				BS 5950	87.8 kN

105.4 kN

EN 1993-1-8



M30 carbor	n steel				
material stre		(N/mm ²)		measured d	iameters (mm)
	Ü	1060		29.91	29.99
		1029		29.95	29.94
		1090		29.93	29.89
Average	-	1060	_	29.94	30.00
J				29.87	30.01
				29.97	29.95
				Average	29.95
Adjustment	factor, $\alpha_{ m v}$	0.945		Shear area	343 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	242.20	228.98			137.2 kN
2	209.98	198.52			
3	212.71	201.10		EN 1993-1-8	8 resistance
4	207.51	196.18			164.6 kN
	Mean	206.19			
Standa	rd deviation	15.32			
Coefficient	of variation	7.4%			
ULS Desig	n resistance	206.2	kN		
				BS 5950	137.2 kN

164.6 kN



Appendix B Test data and resistance calculations – stainless steel shear resistances

M8 stainle	ss steel				
material st	rength	(N/mm^2)		measured di	ameters (mm)
		748		7.97	7.95
		754		7.94	7.97
		756		7.94	7.95
Average	_	753	_	7.96	7.94
				7.96	7.94
				7.96	7.94
				Average	7.95
Adjustmen	t factor, $\alpha_{ m v}$	0.936		Shear area	23.2 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 resi	istance
1	14.93	13.97			6.5 kN
2	14.53	13.60			
3	14.29	13.37		EN 1993-1-4	l resistance
4	14.02	13.12			7.8 kN
	Mean	13.51			
Standa	ard deviation	0.36			
Coefficien	t of variation	2.7%			
	$k_{d,n}$	3.23			
ULS Desig	gn resistance	12.3	kN		
				BS 5950	6.5 kN
				EN 1993-1-8	7.8 kN



M10 stainle	ess steel				
material str	ength	(N/mm^2)		measured di	iameters (mm)
		746		9.96	9.94
		748		9.96	9.96
		751		9.95	9.95
Average	_	748		9.97	9.96
				9.95	9.95
				9.95	9.95
				Average	9.95
Adjustment	factor, $\alpha_{ m v}$	0.940		Shear area	39.6 mm²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 res	istance
1	24.73	23.24	_		11.1 kN
2	24.34	22.87			
3	23.74	22.31		EN 1993-1-4	l resistance
4	23.51	22.09			13.3 kN
	Mean	22.63			
Standa	ard deviation	0.52			
Coefficient	of variation	2.3%			
	$k_{d,n}$	3.23			
ULS Desig	n resistance	20.9	kN		
				BS 5950	11.1 kN
				EN 1993-1-8	13.3 kN



M12 stainle	ess steel				
material str	rength	(N/mm^2)		measured d	liameters (mm)
		775		11.98	11.92
		776		11.96	11.94
		792	_	11.93	11.94
Average	<u>-</u>	781	_	11.94	11.94
				11.95	11.95
				11.95	11.95
				Average	11.95
Adjustment	factor, $\alpha_{\rm v}$	0.900		Shear area	54.9 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	34.40	30.97			15.4 kN
2	34.22	30.81			
3	33.80	30.43		EN 1993-1-	4 resistance
4	33.92	30.54			18.4 kN
	Mean	30.69			
Standa	rd deviation	0.25			
Coefficient	of variation	0.8%			
	$k_{d,n}$	3.23			
ULS Desig	n resistance	29.9	kN		
				BS 5950	15.4 kN

18.4 kN



M16 stainle	ess steel				
material str	ength	(N/mm^2)		measured d	liameters (mm)
		751		15.95	15.96
		747		15.96	15.96
		760		15.95	15.96
Average	-	753	_	15.94	15.95
				15.94	15.95
				15.95	15.97
				Average	15.95
Adjustment	factor, $\alpha_{\rm v}$	0.933		Shear area	107.4 mm ²
		normalised			
	test shear	shear			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 res	istance
1	61.72	57.57	_		30.1 kN
2	61.64	57.49			
3	62.44	58.24		EN 1993-1-	4 resistance
4	60.34	56.28			36.1 kN
	Mean	57.40			
Standa	ard deviation	0.82			
Coefficient	t of variation	1.4%			
	$k_{d,n}$	3.23			
ULS Desig	n resistance	54.8	kN		
				BS 5950	30.1 kN
				EN 1993-1-8	36.1 kN



Appendix C Test data and resistance calculations – carbon steel tensile resistances

M8 carbo	n steel				
material st		(N/mm²)		measured d	iameters (mm)
material 3	aciigai	1155		8.01	7.93
		1149		7.90	7.89
		1145		7.90 7.92	
A.,	-		-		7.98
Average		1156		7.92	7.91
				7.92	7.92
				7.92	7.94
				Average	7.93
Adjustmen	nt factor, $\alpha_{\rm t}$	0.880		tensile area	15.7 mm²
		normalised			
	test tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 res	istance
1	12.43	10.94	_		11.0 kN
2	12.94	11.39			
3	13.06	11.49		EN 1993-1-8	3 resistance
4	13.99	12.31			11.3 kN
5	14.25	12.54			
6	13.11	11.54			
	Mean	11.70			
Stanc	dard deviation	0.60			
Coefficier	nt of variation	5.2%			
	$k_{d,n}$	3.13			
ULS Desi	ign resistance	9.8	kN		
				BS 5950	9.8 kN

BS 5950 9.8 kN EN 1993-1-8 9.8 kN



M10 carbor	n steel				
material str	ength	(N/mm^2)		measured d	iameters (mm)
		997		9.88	9.81
		1009		9.81	9.87
	_	1038	_	9.82	9.87
Average	•	1015	_	9.85	9.83
				9.83	9.81
				9.87	9.87
				Average	9.84
Adjustment	factor, $\alpha_{\rm t}$	1.000		tensile area	30.1 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 res	istance
1	16.08	16.08	_		21.1 kN
2	15.25	15.25			
3	16.12	16.12		EN 1993-1-8	3 resistance
4	15.36	15.36			21.7 kN
5	16.07	16.07			
6	16.94	16.94			
	Mean	15.97			
Standa	rd deviation	0.61			
Coefficient	of variation	3.8%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	14.1	kN		
				BS 5950	14.1 kN

14.1 kN



M12 carbon steel

material st	rength	(N/mm^2)		measured o	diameters (mm)
		1084		11.91	11.82
		1114		11.96	11.97
		1095		11.94	12.03
Average		1098		11.93	11.89
				11.96	11.90
				11.90	11.91
				Average	11.93
Adjustment	factor, α_t	0.922		tensile area	43.7 mm
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	29.03	26.77			30.6 kN
2	27.15	25.04			
3	26.93	24.84		EN 1993-1-	8 resistance
4	27.79	25.63			31.5 kN
5	26.36	24.31			
6	28.86	26.62			
	Mean	25.53			
Standa	ard deviation	0.99			
Coefficient	of variation	3.9%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	22.4	kN		
				BS 5950	22.4 kN

EN 1993-1-8

22.4 kN



M14 carbo	n steel				
material strength		(N/mm^2)		measured o	diameters (mm)
		1065		13.96	13.92
		1069		13.98	13.98
	_	1082	_	13.96	14.00
Average	-	1072		13.98	13.95
				14.00	14.01
				13.98	13.98
				Average	13.98
Adjustmen	t factor, $\alpha_{\rm t}$	0.936		tensile area	58.3 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	39.08	36.59			40.8 kN
2	40.46	37.88			
3	40.87	38.26		EN 1993-1-	8 resistance
4	41.84	39.17			42.0 kN
5	39.56	37.04			
6	39.93	37.38			
	Mean	37.72			
Standa	ard deviation	0.93			
Coefficient	of variation	2.5%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	34.8	kN		
				BS 5950	34.8 kN

34.8 kN



M16 carbor	n steel				
material str	ength	(N/mm^2)		measured o	diameters (mm)
		1174		15.63	15.98
		1197		15.97	15.97
	_	1186	_	15.98	15.99
Average		1186		15.97	15.96
				15.92	15.99
				15.94	15.98
				Average	15.94
Adjustment	factor, α_{t}	0.850		tensile area	87.4 mm²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	56.83	48.29			61.2 kN
2	54.15	46.01			
3	64	54.39		EN 1993-1-	8 resistance
4	56.15	47.71			62.9 kN
5	53.93	45.83			
6	58.45	49.67			
	Mean	48.65			
	rd deviation	3.16			
Coefficient of variation		6.5%			
	k _{d,n}	3.13			
ULS Desig	n resistance	38.8	kN		

BS 5950 38.8 kN EN 1993-1-8 38.8 kN



M20 carbo	n steel				
material st	rength	(N/mm ²)		measured d	iameters (mm)
		1125		19.92	19.98
		1072		19.97	19.99
		1077	_	20.02	20.02
Average	•	1091	_	19.98	19.99
				19.97	20.03
				20.00	20.01
				Average	19.99
Adjustment	t factor, $\alpha_{\rm t}$	0.917		tensile area	134.6 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	82.22	75.41			94.2 kN
2	83.29	76.40			
3	79.78	73.18		EN 1993-1-	8 resistance
4	80.78	74.09			96.9 kN
5	82.44	75.62			
6	82.02	75.23			
	Mean	74.99			
Standa	Standard deviation				
Coefficient	t of variation	1.5%			
k _{d,n}		3.13			
ULS Desig	n resistance	71.4	kN		

BS 5950

EN 1993-1-8

71.4 kN

71.4 kN



M24 carbo	n steel				
material st	rength	(N/mm^2)		measured d	liameters (mm)
		1090		23.91	23.92
		1063		23.88	23.98
	_	1093	_	23.92	23.93
Average	_	1082		23.94	23.93
				23.90	23.92
				23.94	23.92
				Average	23.92
Adjustmen	t factor, $lpha_{ m t}$	0.930		tensile area	191.6 mm²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	133.01	123.71			134.1 kN
2	129.42	120.37			
3	132.43	123.17		EN 1993-1-	8 resistance
4	133.09	123.78			138.0 kN
5	129.06	120.04			
6	130.25	121.14			
	Mean	122.04			
	ard deviation	1.72			
Coefficient of variation		1.4%			
	$k_{d,n}$	3.13			
ULS Design resistance		116.7	kN		

BS 5950

EN 1993-1-8

116.7 kN

116.7 kN



M30 carbor	n steel				
material strength		(N/mm^2)		measured o	diameters (mm)
		1060		29.91	29.99
		1029		29.95	29.94
	_	1090	_	29.93	29.89
Average	-	1060	-	29.94	30.00
				29.87	30.01
				29.97	29.95
				Average	29.95
Adjustment factor, $\alpha_{\rm t}$		0.947		tensile area	287.2 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)		BS 5950 res	sistance
1	187.51	177.59	_		201.0 kN
2	189.49	179.47			
3	189.71	179.68		EN 1993-1-	8 resistance
4	190.08	180.03			206.8 kN
5	190.34	180.27			
6	193.25	183.03			
	Mean	180.01			
Standa	rd deviation	1.76			
Coefficient	of variation	1.0%			
	$k_{d,n}$	3.13			
ULS Desig	n resistance	174.5	kN		
				BS 5950	174.5 kN

174.5 kN



Appendix D Test data and resistance calculations – stainless steel tensile resistances

M8 stainle	ess steel				
material st	material strength			measured d	liameters (mm)
		748		7.97	7.95
		754		7.94	7.97
		756		7.94	7.95
Average	_	753	_	7.96	7.94
				7.96	7.94
				7.96	7.94
				Average	7.95
Adjustmen	It factor, α_{t}	0.941		tensile area	18.7 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 resistance	
1	7.42	6.98	<u> </u>		9.2 kN
2	8.34	7.85			
3	7.44	7.00		EN 1993-1-	4 resistance
4	7.07	6.66			9.4 kN
5	6.81	6.41			
6	8.09	7.62			
	Mean	7.09			
Stand	ard deviation	0.55			
Coefficien	t of variation	7.8%			
	$k_{d,n}$	3.16			
ULS Desig	gn resistance	5.3	kN		
				BS 5950	5.3 kN
				EN 1993-1-4	5.3 kN



M10 stainle	ss steel				
material strength		(N/mm^2)		measured di	ameters (mm)
		746		9.96	9.94
		748		9.96	9.96
		751		9.95	9.95
Average	•	748		9.97	9.96
				9.95	9.95
				9.95	9.95
				Average	9.95
Adjustment factor, $\alpha_{\rm t}$		0.944		tensile area	30.1 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 resi	stance
1					14.7 kN
2	16.18	15.27			
3	16.93	15.98		EN 1993-1-4	resistance
4	16.73	15.79			15.2 kN
5	17.34	16.37			
6	19.33	18.25			
	Mean	16.33			
Standa	rd deviation	1.14			
Coefficient	of variation	7.0%			
	k _{d,n}	3.16			
ULS Desig	n resistance	12.7	kN		
				BS 5950	12.7 kN

12.7 kN



M12 stainle	ess steel				
material str	rength	(N/mm^2)		measured d	liameters (mm)
		775		11.98	11.92
		776		11.96	11.94
	_	792	_	11.93	11.94
Average	-	781	-	11.94	11.94
				11.95	11.95
				11.95	11.95
				Average	11.95
Adjustment factor, $\alpha_{\rm t}$		0.904		tensile area	43.7 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	sistance
1	26.61	24.07			21.4 kN
2	26.87	24.30			
3	25.91	23.43		EN 1993-1-	4 resistance
4	27.36	24.75			22.0 kN
5	25.89	23.42			
6	25.73	23.27			
	Mean	23.87			
Standard deviation		0.59			
Coefficient of variation		2.5%			
	$k_{d,n}$	3.16			
ULS Design resistance		22.0	kN		

BS 5950 21.4 kN EN 1993-1-4 22.0 kN



M16 stainle	ss steel				
material strength		(N/mm^2)		measured d	iameters (mm)
		751		15.95	15.96
		747		15.96	15.96
	_	760	_	15.95	15.96
Average		753		15.94	15.95
				15.94	15.95
				15.95	15.97
				Average	15.95
Adjustment	factor, $\alpha_{\rm t}$	0.935		tensile area	87.4 mm ²
	test	normalised			
	tension	tension			
Test	resistance	resistance			
number	(kN)	(kN)	_	BS 5950 res	istance
1	54.10	50.61			42.8 kN
2	62.60	58.56			
3	56.35	52.71		EN 1993-1-	4 resistance
4	58.51	54.73			44.0 kN
5	53.53	50.08			
6	61.54	57.57			
	Mean	54.04			
Standa	rd deviation	3.54			
Coefficient of variation		6.5%			
	k _{d,n}	3.16			
ULS Desig	n resistance	42.9	kN		
				BS 5950	42.8 kN

42.9 kN

